

# #83 BASE-SEAL COATING



**DESCRIPTION:** Use TopShield PRO #83 Base-Seal Coating to reduce bleedthrough over asphalt surfaces and to enhance adhesion. This waterborne epoxy is formulated for use with TopShield PRO #85 White Silicone Coating.

**PREPARATION:** Surfaces must be clean, dry, and sound. Contaminants such as dirt, dust, grease, wax, oils, soap film, mold & mildew, bond breakers, curing compounds, and loose, peeling paint must be removed before priming. Surfaces with mildew growth or stains must be cleaned with a bleach solution (two parts water to one part bleach) prior to applying this product. Rinse thoroughly. Pressure washing entire surface is recommended for best results (use only a wide fan tip - do not allow stream to tear into roof surface). Prior to application of TopShield PRO #83, repair all cracks, splits or damaged areas using a 3 or 5 course application of TopShield PRO #83 and Polyester Reinforcement. TopShield PRO Seam & Repair Tape may be substituted for repairs as appropriate. For warranted projects, follow job specific specifications. Allow repairs to cure 24 - 72 hours (depending on weather and drying conditions) before application of silicone coating. Asphalt surfaces require a minimum of 8 dry mills of continuous film for bleed-through resistance. Asphalt: The age and condition of asphalt will affect bleed-through with newly applied and uncleaned asphalt surfaces increasing bleed. Do not heat or thin. Single Ply: Do not apply to Single Ply Roof Surfaces. Single Ply roofs must be primed. Metal: Rusty metal must be cleaned with a wire brush and primed/sealed. Application of silicone prior to full cure of TopShield PRO #83 may result in blisters or peeling. **DO NOT APPLY WHEN RAIN OR DEW IS EXPECTED WITHIN 24 - 48 HOURS OF APPLICATION COMPLETION.**

**FOR BEST RESULTS:** Always check weather forecast prior to preparation & application.

**APPLICATION:** For exterior use only. Protective clothing, gloves, and eyewear should be used during application of this product. Always apply on a clear, warm sunny day. Apply in morning hours to allow maximum cure time. Application should be completed a minimum of four hours prior to sunset. Temperatures must be above 55 °F (for 24 hours) and rising, but not above 110 °F ambient. Apply with a 3/4" nap exterior paint roller, brush or professional airless sprayer. Allow to cure a minimum of four hours before applying additional coats of #83. Product fully cures in 24 hours when used as a base coat at 70 °F & 50% max relative humidity. When using polyester reinforcement, full cure is 48 - 72 hours at 70 °F & 50% max relative humidity. Important: Higher humidity, thicker films, poor air flow and lower temperatures will increase dry times.

**COVERAGE RATE:** Base Coat/Primer is 1 gallon per square and is 3 - 4 gallons per square when used with reinforcements. See specifications for additional information.

**SPRAY INFO:** 2000-3000 PSI, .030 - .041 Tip Size, 1-3 GPM.

**NOTE:** Excessive heat can cause flash drying of coating. Not recommended to apply to surfaces 110 °F or greater.

**STORAGE & HANDLING PRECAUTIONS:** Shelf life is two years from date of manufacturer. Do not store at temperatures below 50 °F or above 110 °F. For maximum shelf life store between 60 °F and 80 °F. Keep container sealed when not in use. Always keep covered and protected from the elements. When transporting this product, ensure that lid is tight and pail secured. Do not allow pail to tumble as this may cause lid to loosen and leakage to occur. Do not transport on passenger seats or inside the passenger compartment of any vehicle. Store product in the cargo area of vehicle, and secure over protective cloths to prevent damage due to accidental spills. The manufacturer also disclaims liability for flat surface application where poor drainage or ponding of water may prevail. Do not reuse empty container. Dispose of in an environmentally acceptable manner. Do not use in drinking water or food systems.

**CLEAN-UP:** Clean tools with soap and water.

### TYPICAL PHYSICAL & PERFORMANCE CHARACTERISTICS

Solids by Weight	57%
Tensile Strength (ASTM D2370)	275 psi
Elongation (ASTM D2370)	275%
Weight Per Gallon	10.95 lbs/gal
Bleed Resistance	Excellent
Viscosity	100 - 130 ku
Adhesion	Excellent
Consistency	Brush, Roller, or Spray
Skin Time (50% Relative Humidity, 70°F)	8 hrs.
Full Cure (50% Relative Humidity, 70°F) (Depending on qty & specification)	24 - 72 hrs.
Application Temperatures	55 °F - 110 °F
Clean-up Tools	Warm Water & Soap

\*Specification data may vary +/- 5% from published values

Approx. Shipping Weights (Note: All approx. weights include container)	
1 gallons (3.4L)	11.5 lbs.
5 gallons (18.9L)	58 lbs.
VOC	<10 g/L (regulatory)

# #83

## BASE-SEAL COATING

**STORAGE & HANDLING PRECAUTIONS:** Shelf life is two years from date of manufacturer. Do not store at temperatures below 50 °F or above 110 °F. For maximum shelf life store between 60 °F and 80 °F. Keep container sealed when not in use. Always keep covered and protected from the elements. When transporting this product, ensure that lid is tight and pail secured. Do not allow pail to tumble as this may cause lid to loosen and leakage to occur. Do not transport on passenger seats or inside the passenger compartment of any vehicle. Store product in the cargo area of vehicle, and secure over protective cloths to prevent damage due to accidental spills. The manufacturer also disclaims liability for flat surface application where poor drainage or ponding of water may prevail. Do not reuse empty container. Dispose of in an environmentally acceptable manner. Do not use in drinking water or food systems.

**CLEAN-UP:** Clean tools with soap and water.

**WARRANTY AND DISCLAIMER:** SRS Distribution, Inc. (herein SRS) hereby warrants to the original purchaser, contingent upon original proof of purchase, that this product will be free from any and all manufacturing defects that may materially and adversely affect the product's performance at the time the product is manufactured. Should a manufacturing defect materially and adversely affect this product's performance, SRS shall, within its sole discretion and upon receipt of Purchaser's timely written notice within the Warranty Period, provide replacement product(s) or refund the purchase price of the defective product.

THIS LIMITED WARRANTY IS PURCHASER'S SOLE AND EXCLUSIVE WARRANTY AND REPLACES ALL OTHER WARRANTIES, CONDITIONS, REPRESENTATIONS AND GUARANTEES, WHETHER EXPRESS OR IMPLIED, WHETHER BY STATUTE, AT LAW OR IN EQUITY, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

This limited warranty does not cover labor or installation costs, leaks, or materials not manufactured by OEM supplier, consequential damages or incidental damages. Some states do not allow limitations on how long an implied warranty lasts, so the above limitation may not apply to you. This warranty gives you specific legal rights, and you may also have other rights which vary from state to state. Direct all warranty claims in writing along with original proof of purchase to TopShield PRO, c/o Warranty Claims Department, 7440 State Highway 121. McKinney, TX 75070-2196. The exclusive venue for any legal action arising out of the purchase of this product or this warranty shall be had in a court of competent jurisdiction within Hillsborough County, Florida. Florida law shall govern. For additional Standard Limited Warranty information contact SRS at (855) 569-1550 or at [info@srstopshield.com](mailto:info@srstopshield.com).

©2021 TopShield® PRO

**Manufactured For:**

SRS Distribution, Inc.  
7440 State Hwy 121  
McKinney, TX 75070

See SDS for more information

Scan the QR  
code to access  
additional  
information

